




WOOD COATINGS

MasqueTop W 5000-A

PRODUCT CODE: See Gloss Level Section



DESCRIPTION

MasqueTop W 5000 is a high-end water based versatile industrial topcoat designated for exterior use such as e.g. windows, doors and other exterior exposed wooden objects. The surface dry and cure to a translucent, very hard but still elastic finish allowing the coating system to follow the natural movement of wood.

The topcoat protects the coated elements against general weathering, dirt pick-up and light degradation after being installed and exposed to natural climate conditions.

The product can be applied with various application methods like e.g. manual or robot spraying, disc, high rotation bells, etc

COLOR

Colorless

MasqueTop W 5000-A can be tinted with our range of products MasqueTint W to get a wide range of colors, RAL and NCS are included.

GLOSS LEVEL

Gloss 5 Code: 6910544 – MasqueTop W 5000-A-05

Gloss 30 Code: 6910498 – MasqueTop W 5000-A

APPLICATION

Pre-treatment: The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %. All softwood and non-durable hardwood for exterior use should either be treated with a wood preservative.

Application: Airmix (aircoat) or airless by hand or in automatic spraying equipment.

Application conditions: The product is delivered ready for use. Stir the product well before use. Optimum temperature for products and surroundings: 18-22 °C with relative air humidity of approx. 50 %

Film thickness: 150-300 µm wet

Spraying conditions

Nozzle

Pressure

Air support

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt

Airless flat 0.28 mm	100 – 110 bar	
Airless flat 0.28 mm	80 – 100 bar	1.0 – 1.5 bar

DRYING

Drying times are indicative at 20 °C and 50% relative humidity

Dry to handle: 2 – 3 hours

Dry to sand/recoat: 3 – 4 hours

The drying time can be reduced by use of force drying systems and efficient ventilation

CONSUMPTION

3 - 6 m² /ltr.

CLEANING OF EQUIPMENT

The equipment can be cleaned with water

STORAGE/TRANSPORT

Temperature for storage/transportation: between 5 – 25 °C

Keep containers tightly closed after use.

PACKAGING

Delivered in drums and IBC containers.

DISPOSAL OF WASTE

See information in the Section 13 of the Safety Data Sheet

SAFETY DATA

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.

Classified and Labelled according to 1272/2008 (CLP)

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt