














WOOD COATINGS

# MasquePrimer W 207 White AWC

PRODUCT CODE: 3960717

TYPICAL END USE						APPLICATION METHODS				
 FURNITURES	 OFFICE F.	 BATH / KITCHEN	 INT. DOORS	 PANELS	 MOULDINGS	 SPRAY	 ROLLERS	 VACUUM	 CURTAIN	 MANUAL
<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

## DESCRIPTION

MasquePrimer W 207 White AWC is a premium water based base coat with high thixotropy for varnishing general indoor furniture, interior joinery, including bath and kitchens, and interior doors.

MasquePrimer W 207 White AWC is specially designed for furniture which require high hiding power, soft touch and excellent resistance to stacking (*blocking* resistance). It has fast drying rate and very good sanding.

MasquePrimer W 207 White AWC provides a very good sealing in combination with a low fibre raising.

## COLOR AND TECHNICAL DATA

White Base

### Technical Data

Density: 1.300 – 1.400 g/cm<sup>3</sup>

Viscosity: Approx. 9000 cPs Brookfield at 20 °C

% Solids: 49 – 53 %

% VOC: 4 - 6 %

## APPLICATION

Stir before use.

Application method: Spraying by Air-gun or Airmix

Viscosity: Approx. 9000 cPs Brookfield at 20 °C

No. of layers: 1

Film thickness: 100 – 150 g/cm<sup>2</sup> wet

Application temperature: 15 to 25 °C for wood, air and product at 60 % HR.

Wood moisture: 12 to 15 %

## DRYING

Drying method: Physical

Drying At 23 °C and 60 % HR

Dust free: 15 min

Touch dry: 30 min

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -  
masquelack@masquelack.com – [www.masquelack.com](http://www.masquelack.com)

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – [www.refor.lt](http://www.refor.lt)



Sanding

4 hours

Drying time depends on the application thickness. It can be higher for Woods with high content of resins and for variation of temperature and moisture. The quality of the final product cannot be optimal when the drying conditions (correct temperature and good air movement) were not followed properly.

## CONSUMPTION

---

Approximately from 130 ml/m<sup>2</sup> when an application of one layer of 100 µm wet without lost by spraying.

## CLEANING OF EQUIPMENT

---

It must be cleaned immediately after its use using water or our cleaning thinner WB AQUANET Concentré (Code: 8196040)

## STORAGE/TRANSPORT

---

Product Stability: 6 months in its closed original package.

Storage temperature: Between 5 and 35 °C.

Transport Temperature: The temperature for transport must be above 5 °C and below of 35 °C.

## PACKAGING

---

Delivered in drums and IBC containers.

## DISPOSAL OF WASTE

---

Packages for recycling must be completely empty.

All wastes must be eliminated according to the legislation of the country.

More information in the Section 13 of the Safety Data Sheet.

## SAFETY DATA

---

More information in the Safety Data Sheets which are done according to 1907/2006/CE (REACH) and 2015/830/EU.

Product classified according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.

---

### INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -  
masquelack@masquelack.com – [www.masquelack.com](http://www.masquelack.com)

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – [www.refor.lt](http://www.refor.lt)

