





WOOD COATINGS

## WB Saturateur IGN

Product code: 6910294



### DESCRIPTION

WB Saturateur IGN is a high-end water based industrial wood coating that can be use as base and top-coat for exterior use.

WB Saturateur IGN is a non-filming product which has very wood wetting, perfect adherence and excellent behaviour to blocking.

WB Saturateur IGN offer high-quality finishing with a natural touch of wood and high-end color effect.

By use of WB Saturateur IGN the wood becomes protected due to its outdoors resistance evaluation and checking according to UNE-EN 927-6 for non-filming products.

WB Saturateur IGN can be pigmented with our range of products MasqueTint WT to get a wide range of colors.

### COLOR

Colorless

### GLOSS LEVEL / TECHNICAL DATA

Mat 30

#### Technical Data

Density: 1.000 – 1.100 g/cm<sup>3</sup>

Viscosity: 10 – 12 sec DIN4 at 20 °C

% VOC: 1 – 3 %

% Solids: 13 – 17 %

### APPLICATION

**Pre-treatment:** The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.

**Application:** Spraying or in brush machines. It also can be applied by manually brushing.

**Application conditions:** The product is delivered ready for use but due to evaporation under processing the solid content of the product must be adjusted with water regularly.

Stir the product well before use. Optimum temperature for products and surroundings: 18-22 °C with relative air humidity of approx. 50 %

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

Version: 1  
25/02/2020

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -  
masquelack@masquelack.com – www.masquelack.com

1 of 2

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – [www.refor.lt](http://www.refor.lt)



## DRYING

---

Drying times are indicative at 20 °C and 50% relative humidity

Dry to handle/recoat App. 1 – 2 hours

The drying time can be reduced by use of force drying systems and efficient ventilation

## CONSUMPTION

---

Depending to wood quality and application methods.

In normal conditions, applying 2 layers of 80 g/m<sup>2</sup> the consumption is ca. 6.5 m<sup>2</sup>/L

## CLEANING OF EQUIPMENT

---

The equipment can be cleaned with water.

## STORAGE/TRANSPORT

---

Temperature for storage/transportation: between 5 – 25 °C

Temperature of transport: Temperature along the delivery route must be above 5 °C.

## PACKAGING

---

Delivered in 18 and 190 Kg

## DISPOSAL OF WASTE

---

See information in the Section 13 of the Safety Data Sheet

## SAFETY DATA

---

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.

Classified and Labelled according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.



INDUSTRIAS QUÍMICAS MASQUELACK S.A.

Version: 1  
25/00/2020

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -  
masquelack@masquelack.com – www.masquelack.com

2 of 2

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – [www.refor.lt](http://www.refor.lt)

