





WOOD COATINGS

MasquePrimer 50

PRODUCT CODE: 6910314



DESCRIPTION

MasquePrimer 50 is a white water-based primer for protecting wood of treated woods for outdoor use (class 2 and 3), as is related in BS/EN 335-1, like window frames and doors. It can be also used for wood protections and wood surfaces treated against natural degradation of the wood and by fungi discoloration.

MasquePrimer 50 provides a perfect balance between flow and hiding power, so it is the best product to use when is required a white opaque coat with high quality.

MasquePrimer 50 has been formulated to provide excellent draining properties and to provide an homogeneous surface with very low defibrating which let the surface prepared to apply base coats or top coats.

Using MasquePrimer 50 the treated wood is more stable.

COLOR

White

GLOSS LEVEL AND TECHNICAL DATA

Technical Data

Density: 1.180 – 1.230 g/cm³

% Solids: 38 – 42 %

Viscosity: 16 – 18 sec DIN4 at 20°C

APPLICATION

Pre-treatment: The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %. All softwoods and non-durable hardwoods for outdoor use must be treated with a wood preservative.

Application: Flow coating, dipping, in brush machine, in vacuum or by manual brush/cloth

Application conditions: The product is delivered ready for use but due to evaporation under processing the solid content of the product must be adjusted with water regularly.

Stir the product well before use. Optimum temperature for products and surroundings: 18-22 °C with relative air humidity of approx. 50 %

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt



DRYING

Drying times are indicative at 20 °C and 50% relative humidity

Touch dry / recoating 1 – 2 hours

The drying time can be reduced by use of force drying systems and efficient ventilation

CONSUMPTION

It depends on the quality of the wood and the application method.

CLEANING OF EQUIPMENT

The equipment can be cleaned with water

STORAGE/TRANSPORT

Temperature for storage/transportation: between 5 – 25 °C

Keep containers tightly closed after use.

PACKAGING

Delivered in drums and IBC containers.

DISPOSAL OF WASTE

See information in the Section 13 of the Safety Data Sheet

SAFETY DATA

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.

Classified and Labelled according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.



INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt