





MasqueMid 100

PRODUCT CODE: 6910319



DESCRIPTION

MasqueMid 100 is a water borne industrial intermediate product for new wood designated for exterior use such as windows and doors.

MasqueMid 100 has pore-filling properties when treating hardwood.

COLOR

Colorless

GLOSS LEVEL AND TECHNICAL DATA

-

Technical Data

Density: 1.030 – 1.060 g/cm³

% Solids: 32 – 36 %

Viscosity: Approx. 14 sec DIN4 at 20 °C

APPLICATION

Pre-treatment: The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %. All softwood and non-durable hardwood for exterior use should either be treated with a wood preservative.

Application: To be applied by flow coating or dipping. Due to evaporation, the solid content of the liquid must be adjusted with water regularly.

Application conditions: The product is delivered ready for use. Stir the product well before use. Optimum temperature for products and surroundings: 18-22 °C with relative air humidity of approx. 50 %

Film thickness: Approx. 100 g/m² wet.

DRYING

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt



Drying times are indicative at 20 °C and 50% relative humidity

Dry to handle: App. 2 hours

Dry to sand/recoat: App. 3 hours

The drying time can be reduced by use of force drying systems and efficient ventilation

CONSUMPTION

Approx. 10 m² /ltr.

CLEANING OF EQUIPMENT

The equipment can be cleaned with water

STORAGE/TRANSPORT

Temperature for storage/transportation: between 5 – 25 °C

Keep containers tightly closed after use.

PACKAGING

Delivered in drums and IBC containers

DISPOSAL OF WASTE

See information in the Section 13 of the Safety Data Sheet

SAFETY DATA

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.

Classified and Labelled according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

Version: 2
15/06/2020

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

2 of 2

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt

