





WOOD COATINGS

MasqueMid 200

PRODUCT CODE: 6910323



DESCRIPTION

MasqueMid 200 is a water based versatile industrial intermediate designated to support production of high-end wooden objects as e.g. windows & doors.

The product provides a voluminous surface and gives an excellent foundation for the subsequent layer of topcoat.

MasqueMid 200 is widely used on the wide variety of coarse-grain woods used in the European wooden window manufacturing industry and shows excellent pore-filling properties when treating hardwood.

COLOR

Colorless

GLOSS LEVEL AND TECHNICAL DATA

-

Technical Data

Density: 1.020 – 1.040 g/cm³

% Solids: 28 – 32 %

APPLICATION

Pre-treatment: The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %. All softwood and non-durable hardwood for exterior use should either be treated with a wood preservative.

Application: Airmix (aircoat) or airless by hand or in automatic spraying equipment

Application conditions: The product is delivered ready for use but up to 5% water could be added if needed. Stir the product well before use. Optimum temperature for products and surroundings: 18-22 °C with relative air humidity of approx. 50 %

Film thickness: 150-225 g/m² wet

Spraying conditions

Nozzle	Pressure	Air support
Airless flat 0.28 mm	100 – 110 bar	
Airmix flat 0.28 mm	80 – 100 bar	1.0 – 1.5 bar

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt



DRYING

Drying times are indicative at 20 °C and 50% relative humidity

Dry to handle: App. 2 hours
Dry to sand/recoat: App. 3 hours

The drying time can be reduced by use of force drying systems and efficient ventilation

CONSUMPTION

3 - 6 m² /ltr.

CLEANING OF EQUIPMENT

The equipment can be cleaned with water

STORAGE/TRANSPORT

Temperature for storage/transportation: between 5 – 25 °C
Keep containers tightly closed after use.

PACKAGING

Delivered in drums and IBC containers

DISPOSAL OF WASTE

See information in the Section 13 of the Safety Data Sheet

SAFETY DATA

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.
Classified and Labelled according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.



INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt