




WOOD COATINGS

MasquePrimer W 47

PRODUCT CODE: 6910451



DESCRIPTION

MasquePrimer W 47 is a water borne industrial primer for new wood designated for exterior use such as fences and cladding.

MasquePrimer W 47 minimises yellowing from knots and softwood with a large amount of heartwood.

COLOR

White

GLOSS LEVEL AND TECHNICAL DATA

-

Technical Data

Density: 1.310 – 1.350 g/cm³

% Solids: 49 – 53 %

Viscosity: Approx. 15 sec DIN4 at 20 °C

APPLICATION

Pre-treatment: The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.

All softwood for exterior use should either be vacuum impregnated or treated with a wood preservative.

Application: To be applied by flow coating or dipping. Due to evaporation, the solid content of the liquid must be adjusted with water regularly.

Application conditions: The product is delivered ready for use.

Film thickness—achieved by 1 x flow coat: 100 µm wet.

Stir the product well before use. Optimum temperature for products and surroundings: 18-22 °C with relative air humidity of approx. 50 %

Paint system: Primer wood should be treated with a topcoat before being exposed to the weather.

INDUSTRIAS QUÍMICAS MASQUELACK S.A

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt



DRYING

Drying times are indicative at 20 °C and 50% relative humidity

Dry to handle:	1 – 2 hours
Dry to sand/dry to recoat:	2 – 3 hours

As the layer thickness is of paramount importance for the effectiveness of the product, it is important not to sand the surface too much.

The drying time can be reduced by use of force drying systems and efficient ventilation

CONSUMPTION

Ca. about 10 m²/L

CLEANING OF EQUIPMENT

The equipment can be cleaned with water

STORAGE/TRANSPORT

Temperature for storage/transportation: between 5 – 25 °C
Keep containers tightly closed after use.

PACKAGING

Delivered in drums and IBC containers.

DISPOSAL OF WASTE

See information in the Section 13 of the Safety Data Sheet

SAFETY DATA

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.
Classified and Labelled according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.

INDUSTRIAS OUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt