





WOOD COATINGS

# MasqueWoodOil

PRODUCT CODE: 6910496



## DESCRIPTION

MasqueWoodOil is a water bornel industrial intermediate product for new wood designated for exterior use such as windows and doors.

MasqueWoodOil has pore-filling properties when treating hardwood.

## COLOR

Colorless

## GLOSS LEVEL AND TECHNICAL DATA

-

### Technical Data

Density: 1.050 – 1.080 g/cm<sup>3</sup>

% Solids: 31 – 35 %

Viscosity: Approx 6000 cPs at 20 °C

## APPLICATION

**Pre-treatment:** The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %. All softwood and non-durable hardwood for exterior use should either be treated with a wood preservative.

**Application:** Airmix (aircoat) or airless by hand or in automatic spraying equipment

**Application conditions:** The product is delivered ready for use. Stir the product well before use. Optimum temperature for products and surroundings: 18-22 °C with relative air humidity of approx. 50 %

**Film thickness:** Approx. 150 microns wet

### Spraying conditions

| <u>Nozzle</u>           | <u>Pressure</u> | <u>Air support</u> |
|-------------------------|-----------------|--------------------|
| Airless flat<br>0.28 mm | 100 – 110 bar   |                    |
| Airless flat<br>0.28 mm | 80 – 100 bar    | 1.0 – 1.5 bar      |

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -  
masquelack@masquelack.com – [www.masquelack.com](http://www.masquelack.com)

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – [www.refor.lt](http://www.refor.lt)



## DRYING

---

Drying times are indicative at 20 °C and 50% relative humidity

|                     |              |
|---------------------|--------------|
| Dry to handle:      | App. 2 hours |
| Dry to sand/recoat: | App. 3 hours |

The drying time can be reduced by use of force drying systems and efficient ventilation

## CONSUMPTION

---

Approx. 6 m<sup>2</sup> /ltr.

## CLEANING OF EQUIPMENT

---

The equipment can be cleaned with water

## STORAGE/TRANSPORT

---

Temperature for storage/transportation: between 5 – 25 °C  
Keep containers tightly closed after use.

## PACKAGING

---

Delivered in drums and IBC containers

## DISPOSAL OF WASTE

---

See information in the Section 13 of the Safety Data Sheet

## SAFETY DATA

---

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.  
Classified and Labelled according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.

---

### INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -  
masquelack@masquelack.com – [www.masquelack.com](http://www.masquelack.com)

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – [www.refor.lt](http://www.refor.lt)

