





WOOD COATINGS

MasqueSeal W 50

PRODUCT CODE: 6910616



DESCRIPTION

MasqueSeal W 50 is a water borne sealer intended for temporary protection of LVL.

The product provides superior water repellency and minimizes moisture ingress into the wooden surface.

Despite of the hydrophobic nature of the product it is still recoatable with water borne latex based paint. It can also be glued.

COLOR

Colourless

GLOSS LEVEL AND TECHNICAL DATA

N.A.

Technical Data

Density: 1.00 – 1.05 g/cm³
Viscosity: 10 – 15 sec DIN4 at 20 °C
% VOC: 0 – 2 %
% Solids: 3 – 6 %

APPLICATION

Application: Spraying or in brush machines. It also can be applied by manually brushing.

Application conditions: The product is delivered ready for use

Stir the product well before use. Optimum temperature for products and surroundings: 18-22 °C with relative air humidity of approx. 50 %

DRYING

Due to low solid content and good penetration the product dries very fast.

The drying time can be reduced by use of force drying systems and efficient ventilation

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt



CONSUMPTION

Application amount is 50-100 g/m², 10 – 20 ml/m²

CLEANING OF EQUIPMENT

The equipment can be cleaned with water or using our cleaner WB AQUANET Concentré (Code: 8196040)

STORAGE/TRANSPORT

Temperature for storage/transportation: between 5 – 25 °C
Temperature of transport: Temperature along the delivery route must be above 5 °C.

PACKAGING

Delivered in 20 ltr cans, drums and IBC containers.

DISPOSAL OF WASTE

See information in the Section 13 of the Safety Data Sheet

SAFETY DATA

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.
Classified and Labelled according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt

