





WOOD COATINGS

# MasquePrimer W 150 Clear

PRODUCT CODE: 6910648



## DESCRIPTION

Two-component water-borne primer for new wood designated for exterior use such as windows and doors.

MasquePrimer W 150 Clear reduces yellowing from knots and softwood with a large amount of heartwood.

## COLOR

White (colorless once dried)

## GLOSS LEVEL / TECHNICAL DATA

N.A.

### Technical Data:

Density: 1.020 – 1.060 g/cm<sup>3</sup>

% Solids: 28 – 32 %

% VOC: 4 – 6 %

## APPLICATION

Stir well before use.

Application mode: Air-gun, Airless and Airmix.

Number of layers: 1

Thickness per layer: 150 - 200 um wet

Application temperature: 15 to 25 °C for wood, air and product at 50 % RH.

Wood moisture: 12 - 15 %

## DRYING

Drying: Physical and Chemical

Mixture ratio (by volume) 2.1 parts of MasquePrimer W 150 Clear  
1 part of MasqueHard W 150 (Code: 6910632)

Mixture ratio (by weight) 2.6 parts of MasquePrimer W 150 Clear  
1 part of MasqueHard W 150 (Code:  
6910632)

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -  
masquelack@masquelack.com – [www.masquelack.com](http://www.masquelack.com)

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – [www.refor.lt](http://www.refor.lt)



Pot-life: 8 hours

At 23 °C and 50% RH

Dry to handle: 2 hours

Overcoating: 4 hours

The drying time can be reduced by use of force drying systems and efficient ventilation

## CONSUMPTION

---

5-7 m<sup>2</sup>/L - Depending on wood quality and application methods.

## CLEANING OF EQUIPMENT

---

The equipment can be cleaned with water or using our thinner WB AQUANET Concentré (Code: 8196040)

## STORAGE/TRANSPORT

---

Temperature for storage/transportation: between 5 – 25 °C

Transport temperature must not be lower than 5 °C.

## PACKAGING

---

Delivered in drums and IBC containers

## DISPOSAL OF WASTE

---

See information in the Section 13 of the Safety Data Sheet

## SAFETY DATA

---

More information and relevant data are stated in Safety Data Sheet according to 1907/2006/CE (REACH) and 2015/830/EU.

Classified and Labelled according to 1272/2008 (CLP)

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.

---

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -  
masquelack@masquelack.com – [www.masquelack.com](http://www.masquelack.com)

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – [www.refor.lt](http://www.refor.lt)