



WOOD COATINGS

MasqueTop W 750

TYPOWE						METODY NAKŁADANIA				
<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>

DESCRIPTION

MasqueTop W 750 is a water borne clear lacquer for surface treatment of furniture for indoor use.

MasqueTop W 750 can be used as a multi-layer product.

MasqueTop W 750 has fast drying, extraordinary high transparency which provides a natural warm look on especially dark wood species, high chemical resistance (R2, according to IOS-MAT-0066), provides an excellent blocking resistance when stacking. The surface is left with a silky-smooth touch although still hard, robust and scratch resistant.

COLOUR AND TECHNICAL DATA

Colour: Transparent
Density: Approx 1.05 g/ml
Solid Content: 32 ± 2 % by weight
% VOC: 4 – 6 %
Viscosity: 60 ± 5 sec DIN4 at 20 C

GLOSS LEVEL

Gloss 75 Code: 5900138 – MasqueTop W 750-G

Semi Mat 40 Code: 5900134 – MasqueTop W 750-4

Mat 20 Code: 5900129 – MasqueTop W 750-2

Mat 10 Code: 5900128 – MasqueTop W 750-1

High Mat 5 Code: 5900137 – MasqueTop W 750-05

APPLICATION

Stir before use.

Application method: Spraying by Air-gun or Airmix. In some cases, it can be applied manually.

Viscosity: 55 – 65 sec DIN4 at 20 rC

No. of layers: 2

Film thickness: 120 μ wet

Application temperature: 15 to 25 rC for wood, air and product at 60 % HR

Wood moisture: 12 to 15 %

INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt



DRYING

Drying method: Physical			
Drying	At 23 °C and 60 % HR	At 40 °C and 60 % HR	After forced drying, samples should be cooled to 25 °C before stacking.
Dust free:	15 min	10 min	
Touch dry:	30 min	15 min	
Sanding	1 hours	15 min	
Stacking:	3 hours	1 hour	

Drying time depends on the application thickness. It can be higher for woods with high content of resins and for variation of temperature and moisture. The quality of the final product cannot be optimal when drying conditions (correct temperature and good air movement) are not followed properly.

CONSUMPTION

Approximately 120 ml/m² when applying one layer of 120 µm wet without any loss by spraying.

CLEANING OF EQUIPMENT

It must be cleaned immediately after its use, using water or our cleaning thinner WB AQUANET Concentré (Code: 8196040)

STORAGE/TRANSPORT

Product Stability: 6 months in its closed original package.
Storage Temperature: Between 5 and 35 °C.
Transport Temperature: The temperature for transport must be above 5 °C and below of 35 °C

PACKAGING

Delivered in 20 KG.

DISPOSAL OF WASTE

Packages for recycling must be completely empty.
All wastes must be eliminated according to the legislation of the country.
More information in the Section 13 of the Safety Data Sheet.

SAFETY DATA

More information in the Safety Data Sheets which are done according to 1907/2006/CE (REACH) and 2015/830/EU.
Product classified according to 1272/2008 (CLP).

The given information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Masquelack.



INDUSTRIAS QUÍMICAS MASQUELACK S.A.

C/ De Pedrosa, 26-28. 08783 Masquefa – Barcelona – España -
masquelack@masquelack.com – www.masquelack.com

Representative in Lithuania – Refor UAB, Raudondvario pl. 242C, LT-47158, Kaunas – www.refor.lt

